

FLINTBOND®

SBS Modified Bitumen Caulk Grade Adhesive

Product Information



Description: FlintBond SBS Modified Bitumen Caulk Grade Adhesive is a professional grade, polymer modified flashing cement specially formulated for use with modified bitumen membranes, base sheets and ply sheets. FlintBond SBS Modified Bitumen Caulk Grade Adhesive is manufactured using select asphalt, rubber, solvent and fibers. It provides excellent elongation and recovery properties, plus enhanced adhesive properties and durability. It is ideal for seams, flashings and repairs on SBS modified membranes. FlintBond SBS Modified Bitumen Caulk Grade Adhesive is also excellent for repairs on conventional built up roofing membranes where movement is expected to occur. FlintBond SBS Modified Bitumen Caulk Grade Adhesive eliminates burn hazards associated with hot kettles and propane torches, and is ideal where their use is prohibited. NOTE: This product is formulated for repairs and seams on SBS asphalt modified roll roofing sheets. DO NOT USE ON APP, TPO, EPDM, PVC or other single ply membranes.

Product Advantages:

1. UL Listed
2. Excellent cure
3. Tough, flexible, adhesive and cohesive film
4. Excellent water and weather resistance
5. Outstanding general adhesive
6. Excellent lap cement
7. Good U.V. resistance
8. Easy to apply
9. Asbestos-free
10. Elastomeric, flexible, withstands stress

Typical Physical Properties

CHARACTERISTIC	RESULT
Weight per tube ASTM D1475	10.3 oz.
Solids by Weight ASTM D1644	72%
Solids by Volume ASTM D2697	68%
Color	Black
% Asphalt Content ASTM D4125	50%
Shear Strength ASTM D3983	26 lbs./sq. in.
Peel Strength ASTM D1876	13 lbs./lin. in.
Cure Time	24 to 48 hrs.
Performance Temp. Range	-40°F to 180°F
Application Temp. Range	50°F to 120°F
Elongation ASTM D412	250%

CHARACTERISTIC	RESULT
Recovery ASTM D412	95%
Consistency, Brookfield RVF Viscometer, #5 Spindle @ 20 RPM @ 77°F ASTM D2196	800,000 Centipoise
Wet Mil Thickness	Caulk Grade N/A

Meets or exceeds ASTM D3019, Type III
U.L. Listed: File #R11656; Control #63P6
Miami-Dade Approved



Packaging

	FLINTBOND CAULK GRADE
Packaging	10.3-oz. tubes
Units Per	12 tubes/carton
Approx. Wt. Per Pallet	1,480 lbs.

Product Application

Preparation: All surfaces must have proper drainage and be clean and free of surface rust and any other foreign matter. Excessive particulate surfacing materials on modified membranes must be removed (sweeping with a stiff broom is recommended) prior to application. On reroofing applications, all deck and existing membrane repairs should be made first. Severely weathered BUR membranes may require a pre-application of FlintPrime™ Asphalt Primer. Metal surfaces must have all rust and scale removed. DO NOT HEAT OR THIN.

Application: Protective clothing and eyewear should be used during application of this product. Apply with trowel or putty knife, working material to an even consistency over and into the area to be repaired. Apply 1/8" to 1/4" thick, two to inches beyond the problem area. For cracks or holes 1/4" to 3/4" wide, press a strip of asphalt saturated fabric into the cement and cover with an additional layer of flashing cement. Form a cant with the cement around chimneys and other roof projections. Coverage rate is approximately 12-1/2 sq. ft. per gallon when applied 1/8" thick.

For Best Results: Cut the modified bitumen sheets to a maximum of 18' lengths and allow to relax on the job site before application. Apply on clear sunny day when surface temperatures are between 50° and 120°F. After a minimum of 45 days cure time, apply a reflective coating. This will greatly extend the life of the roof.

Clean-Up: Clean tools with paint thinner or mineral spirits.

Storage

In colder weather product should be stored in heated room (65° to 80°F) at least 24 hours prior to application.

Technical Assistance

CertainTeed provides technical assistance in the selection, specification and application guidelines for all CertainTeed Commercial Roofing products and systems. Architectural and field representatives are available for consultation within each region. Refer also to the CertainTeed Commercial Roof Systems Specification Manual for additional information.

ASK ABOUT OUR OTHER CERTAINTEED PRODUCTS AND SYSTEMS:

EXTERIOR: ROOFING • SIDING • WINDOWS • FENCE • RAILING • TRIM • DECKING • FOUNDATIONS • PIPE
INTERIOR: INSULATION • WALLS • CEILINGS

CertainTeed Corporation
P.O. Box 860
Valley Forge, PA 19482

Professional: 800-233-8990
www.certainteed.com

CertainTeed 