



22-15 ECO-HANGER GRIP ADHESIVE Lo VOC

COLOR

Brown

SERVICE TEMPERATURE

-20°F TO 225°F
(-29°C TO 106°C)

COVERAGE

Approx. 80 to 100 2"x2" hangers per 1/10th gal tube (.32 Liter Tube), 800-1000 2" x 2 " hangers per gallon

BONDING TIME

0 To 4 Minutes

WEIGHT PER GALLON

10.1 lbs./gal.

AVERAGE NONVOLATILE

61 % by weight

DRYING TIME

Up to 24-48 hours, depending on drying conditions.

SAFETY

Flammable when wet.

Flash Point 0°F < (-18°C)

Red Label

THRESHOLD LIMIT VALUE OF SOLVENT VAPOR

(TLV):100 ppm

LIMITATIONS

Do not apply below 40°F (4°C)

Some plastic foams may be attacked by the solvent in this product. Test before using.

22-15 Eco-Hanger Grip Lo VOC should not be used on wood surfaces or on painted or coated surfaces.

WARNING

CAUTION: FLAMMABLE MIXTURE RED LABEL.

Do not use or store near sparks, heat or open flame. Keep container closed when not in use. Use with adequate ventilation. Avoid prolonged or repeated breathing of vapor or contact with skin. Do not take internally. In an emergency, call a physician. Keep out of reach of children.

DESCRIPTION

22-15 Eco-Hanger Grip Adhesive Lo VOC is a construction type paste adhesive specially designed for bonding insulation hangers to metal ducts, and unfinished masonry surfaces.

22-15 Eco-Hanger Grip Adhesive Lo VOC dries to a tough, yet resilient bond that withstands thermal cycling and shock.

22-15 Eco-Hanger Grip Adhesive Lo VOC has been specially formulated to meet reduced VOC requirements.

APPLICATION

This product is for industrial use only. It should be applied by trained and qualified craftspeople. Be sure surfaces are clean, dry and oil free. Extrude (a bead) approx. 1/16" (1.6MM) thick coat of **22-15 Eco-Hanger Grip Adhesive Lo VOC** to the base of the hanger with caulking gun or apply the adhesive with a spatula, putty knife, small trowel or brush. Immediately press the hanger into place with a twisting motion. Make sure good contact is made. Always prepare and bond only one hanger at a time.

Allow minimum 24-48 hours drying time before applying insulation.

SPECIFICATION COMPLIANCE

ASTM E84

Standard Test Method For Surface Burning Characteristics of Building Materials (ANSI 2.5, NFPA 255, UBC 8-1, UL 723)

Applied to Inorganic Reinforced Cement Board

Flame Spread 0

Smoke Developed 0

Adhesive applied in approximate 2 inch x 2 inch squares every 12 inches on center.

CLEANUP –Mineral spirits or toluol.

VOC= 1.56 lbs./gal or 187 grams/liter

ASBESTOS FREE

03/09

WARRANTY TERMS: The physical and chemical properties of this product are representative of the typical average values derived in accordance with test methods deemed acceptable, and can vary when subjected to normal manufacturing methods. These values are supplied only as a technical service and are subject to change without notice. To be sure information is current call Mon-Eco Industries, Inc.

Terms of Warranty: Warrantor, Mon-Eco Industries, Inc. warrants satisfactory results of this product only when recommendations herein established are followed. The recommendations for use are established upon tests and information deemed reliable. We recommend that adequate testing be made by the user to determine if the product is suitable for the intended purpose and use. Warrantor assumes no responsibility beyond replacement or refund of the purchase price of this product, since warrantor has no control over the methods and application of its product, methods and conditions of transportation, handling and storage of the product. **WARRANTOR EXPLICITLY DISCLAIMS ALL LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGE.** No agent or representative of Mon-Eco Industries, Inc. has the authority to change or extend these conditions.

MON-ECO INDUSTRIES, INC.

5 JOANNA COURT•EAST BRUNSWICK, NJ 08816 (732) 257-7942 • 800-899-6326 • FAX (732) 257-6525

Email: moneco.mei@verizon.net www.mon-ecoindustries.com

