



EDGE HARDNER 88-01

COLOR

Wet: White

Dry: Clear

WEIGHT PER GALLON

9 lbs.

AVERAGE NONVOLATILE

55%

DRYING TIME

Drying depends on the conditions and the degree of penetration and saturation. At least 24 hours of good drying conditions are required to harden the edge. 48 hours of drying time is the norm.

SAFETY

Wet: Non-Flammable

Dry: If tested in accordance with U.S. Std. 723, at a coverage rate of 200 sq./ft./gallon, the Flame Spread is under 25 and the Smoke Development is under 50.

CAUTION

Use with adequate ventilation. Avoid prolonged or repeated breathing of vapor. Avoid prolonged or repeated contact with skin. DO NOT TAKE INTERNALLY. In case of emergency, call a physician. Keep out of reach of children.

SHELF LIFE

One (1) year in unopened containers.

DESCRIPTION

Edge Hardner 88-01 is a water based penetrating sealer designed to efficiently stiffen edges of fiberglass insulation panels. This is an alternative method to using strips, channels and frames.

APPLICATION METHOD

Dip, spray, brush, roll.

APPLICATION INSTRUCTIONS

The Edge Hardner 88-01 is best applied by dipping. A shallow pan fabricated from a rain gutter works nicely. Place 88-01 in the pan. Dip the panel into a depth of one inch. Remove it and repeat the process. Stack the panels to dry. Separate the panels or sticking may occur.

To brush, roll or spray, stack the boards with the edges even. Apply the 88-01 to saturate the edge. Separate the panels to dry.

A satisfactory penetration is to a depth of 1/8" and 1" from the edge. This will dry to form a hard rigid edge.

LIMITATIONS

Keep from freezing. Apply when temperatures are between 50°F and 100°F. Bring material to room temperature before using.

ASBESTOS FREE

Warranty Terms: The physical and chemical properties of this product are representative of the typical average values derived in accordance with test methods deemed acceptable, and can vary when subjected to normal manufacturing methods. These values are supplied only as a technical service and are subject to change without notice. To be sure information is current call Mon-Eco Industries, Inc.

Terms of Warranty: Warrantor, Mon-Eco Industries, Inc. warrants satisfactory results of this product only when recommendations herein established are followed. The recommendations for use are established upon tests and information deemed reliable. We recommend that adequate testing be made by the user to determine if the product is suitable for the intended purpose and use. Warrantor assumes no responsibility beyond replacement or refund of the purchase price of this product, since warrantor has no control over the methods and application of its product, methods and conditions of transportation, handling and storage of the product. WARRANTOR EXPLICITLY DISCLAIMS ALL LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGE. No agent or representative of Mon-Eco Industries, Inc. has the authority to change or extend these conditions.

Mon-Eco Industries, Inc.

5 Joanna Court • 800-899-6326 • East Brunswick, NJ 08816 732 257-7942 Fax: 732-257-6525