



ECO-SPRAY ADHESIVE 22-00

COLORS

Amber

SERVICE TEMPERATURE

-40°F to 180°F (-40°C to 82°C)

COVERAGE

400 sq. ft./gal. (.1 liter/M2)

AVERAGE NON-VOLATILE

22% by weight

BONDING TIME

1 to 6 minutes

The drying time depends on the temperature, humidity and film thickness.

SAFETY

Wet – Flammable

Dry –When tested in accordance with ASTM E-84 the flame spread is < 25 and the smoke development is < 50.

WARNING

Flammable mixture. Do not use or store near heat, sparks, or open flame. Use with adequate ventilation. Avoid prolonged or repeated breathing of the vapor or contact with skin. Do not take internally. In an emergency contact a physician. Keep out of reach of children.

MAX VOC=4.61 lbs./gal; 553 grams/liter

DESCRIPTION

An economical, yet fast tacking, flammable solvent thinned duct liner adhesive.

SPECIFICATION COMPLIANCE

ASTM C916 T-IV

METHOD OF APPLICATION

Spray

APPLICATION

This product is for industrial use only. It should be applied by trained and qualified craftspeople.

Be sure surfaces are clean and dry.

Apply 22-00 in a thin uniform coat. Press the insulation firmly in place. There is adequate open time for normal shop application.

CLEAN UP

Mineral spirits.

Warranty Terms: The physical and chemical properties of this product are representative of the typical average values derived in accordance with test methods deemed acceptable, and can vary when subjected to normal manufacturing methods. These values are supplied only as a technical service and are subject to change without notice. To be sure information is current call Mon-Eco Industries, Inc.

Terms of Warranty: Warrantor, Mon-Eco Industries, Inc. warrants satisfactory results of this product only when recommendations herein established are followed. The recommendations for use are established upon tests and information deemed reliable. We recommend that adequate testing be made by the user to determine if the product is suitable for the intended purpose and use. Warrantor assumes no responsibility beyond replacement or refund of the purchase price of this product, since warrantor has no control over the methods and application of its product, methods and conditions of transportation, handling and storage of the product. WARRANTOR EXPLICITLY DISCLAIMS ALL LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGE. No agent or representative of Mon-Eco Industries, Inc. has the authority to change or extend these conditions.

Mon-Eco Industries, Inc.

5 Joanna Court • 800-899-6326 • East Brunswick, NJ 08816 732 257-7942 Fax: 732-257-6525