



A.V. B. MASTIC

33-20

COLOR

Black

SERVICE TEMPERATURE

-20 to 220°F
(-28.9 to 93°C)

WATER VAPOR TRANSMISSION

Vapor barrier mastic

.01 Perm

COVERAGE

.125" wet film equals 12.8 sq. ft. (3.2 Liter/M²). The coverage rate is dependent on the surface being covered and the application method.

WEIGHT PER GALLON

9.5 lb. (1.13 Kilo/Liter)

AVERAGE NONVOLATILE

75% by weight.

DRYING TIME

Touch: 4 hrs.

Through: 4 days minimum

The drying time depends on the temperature, humidity and film thickness.

SAFETY

Flammability:

Wet: Flash point 120°F (49°C)

Dry: Slow burning.

Threshold limit value of solvent vapor (TLV): 200

ppm.

CAUTION:

Combustible mixture. Keep away from heat, sparks, and open flame. Use with adequate ventilation. Avoid prolonged or repeated breathing of vapor. Avoid prolonged or repeated contact with skin. In an emergency, call a physician. Keep out of reach of children.

WARRANTY TERMS: The physical and chemical properties of this product are representative of the typical average values derived in accordance with test methods deemed acceptable, and can vary when subjected to normal manufacturing methods. These values are supplied only as a technical service and are subject to change notice. To be sure information is current call Mon-Eco Industries, Inc.

Terms of Warranty: Warrantor, Mon-Eco Industries, Inc. warrants satisfactory results of this product only when recommendations herein established are followed. The recommendations for use are established upon tests and information deemed reliable. We recommend that adequate testing be made by the user to determine if the product is suitable for the intended purpose and use. Warrantor assumes no responsibility beyond replacement or refund of the purchase price of this product, since warrantor has no control over the methods and application of its product, methods and conditions of transportation, handling and storage of the product. WARRANTOR EXPLICITLY DISCLAIMS ALL LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGE. No agent or representative of Mon-Eco Industries, Inc. has the authority to change or extend these conditions.

DESCRIPTION

33-20 A.V.B. Mastic is a basic asphalt cut-back mastic designed to provide weather protection for thermal insulation. A.V.B. Mastic can be brush or spray applied. It dries to form a tough black vapor barrier protective film that provides excellent service in chemical and industrial atmospheres.

LIMITATIONS

The solvent in 33-20 may attack plastic foams. Not for use with PVC products. Test before using. Not for use in food storage areas.

33-20 should dry through before top coating.

METHOD OF APPLICATION

Brush or spray with mastic equipment.

MATERIAL PREPARATION

Do not thin.

APPLICATION

This product is for industrial use only. It should be applied by trained and qualified craftspeople.

Prime dusty surfaces. Be sure surfaces are clean and dry. Apply a light tack coat. Imbed a reinforcing membrane. Apply a finish coat of at least 13 sq. ft./gal. (3.2 Liter/M²)

CLEANUP

Mineral spirits.

ASBESTOS FREE

MAX V.O.C.=2.5 lbs/gal; 300 gms/Liter

MON-ECO INDUSTRIES, INC.

5 JOANNA COURT•EAST BRUNSWICK, NJ 08816 (732) 257-7942 • 800-899-6326 • FAX (732) 257-6525

www.mon-ecoindustries.com

