



ECO-MASTIC CORK FILLED 55-61

COLOR

55-61 Gray

SERVICE TEMPERATURE

0 to 180°F
(17.8 to 82°C)

COVERAGE

1/8" wet film = 8 gal./100 sq. ft.
1/4" wet film = 16 gal./100 sq. ft.

The coverage is dependent on the surface being covered and the application method.

WEIGHT PER GALLON

9.1 lb.

AVERAGE NONVOLATILE

57% by weight
70% by volume

DRYING TIME

8 gal./100 sq. ft. Touch: 2 hrs.
Through: 48 hours

The drying time depends on the temperature, humidity, and film thickness.

SAFETY

Flammability:
Wet: Nonflammable.
Dry: Fire resistive

ASBESTOS FREE

CAUTION:

Use with adequate ventilation. Avoid prolonged or repeated breathing of vapor. Avoid prolonged or repeated contact with skin. Do not take internally. In case of emergency, call a physician. Keep out of reach of children.

VOC=0.47 lbs/gal. or 56 grams/liter

DESCRIPTION

55-61 Eco Mastic Cork Filled is a mastic containing a blend of granulated cork. It is designed to provide some condensation control and insulation value where conditions are not too severe. It may be used on tanks and piping where standard insulation isn't practical.

LIMITATIONS

Do not apply below 40°F (4.4°C) and 100°F (38°C) Keep from freezing.

METHOD OF APPLICATION

Glove, spray.

MATERIAL PREPARATION

Do not thin.

APPLICATION

This product is for industrial use only. It should be applied by trained and qualified craftspeople. Be sure surfaces are dry and clean. Prime steel surfaces with a flat corrosion-inhibitive primer. For best results build up thickness with multiple coats allowing 24 hours drying between. However, 1/4" wet film can be applied in one coat. Trowel or glove in even strokes to prevent excessive working of material. Spray apply with air atomizing mastic spray equipment.

CLEANUP

Clean, fresh water.

Warranty Terms: The physical and chemical properties of this product are representative of the typical average values derived in accordance with test methods deemed acceptable, and can vary when subjected to normal manufacturing methods. These values are supplied only as a technical service and are subject to change without notice. To be sure information is current call Mon-Eco Industries, Inc.

Terms of Warranty: Warrantor, Mon-Eco Industries, Inc. warrants satisfactory results of this product only when recommendations herein established are followed. The recommendations for use are established upon tests and information deemed reliable. We recommend that adequate testing be made by the user to determine if the product is suitable for the intended purpose and use. Warrantor assumes no responsibility beyond replacement or refund of the purchase price of this product, since warrantor has no control over the methods and application of its product, methods and conditions of transportation, handling and storage of the product. WARRANTOR EXPLICITLY DISCLAIMS ALL LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGE. No agent or representative of Mon-Eco Industries, Inc. has the authority to change or extend these conditions.

Mon-Eco Industries, Inc.

5 Joanna Court • 800-899-6326 • East Brunswick, NJ 08816 732 257-7942 Fax: 732-257-6525