


IPS Fittings Fabricated 45° Lateral Wye - Three Segment




IPS
HDPE
Fittings

Pressure Rating of Fab Wye is based pipe DR (Wall thickness) and resin properties.

Wyes from 3608 resin:	
DR	Pressure Rating
7	89 psi
9	67 psi
11	53 psi
13.5	43 psi
15.5	37 psi
17	33 psi
21	27 psi
26	21 psi
32.5	17 psi

Wyes from 4710 resin:	
DR	Pressure Rating
7	112 psi
9	84 psi
11	67 psi
13.5	54 psi
15.5	46 psi
17	42 psi
21	34 psi
26	27 psi
32.5	21 psi

Note: Size/DR listings shown are commonly requested. Many DR options not listed are available. Please consult an ISCO representative for availability.



Nominal Size (in)	Pipe OD (in)	DR	Part #	Dimensions			Weight (lbs)	Shipping Method
				L (in)	H (in)	FC (in)		
2	2.375	07	ISFFWY0207IPS	25	5.8	17.5	3	FedEx
3	3.5	07	ISFFWY0307IPS	25	6.78	18.7	7	FedEx
		11	ISFFWY0311IPS	"	"	"	5	"
4	4.5	07	ISFFWY0407IPS	26.5	5.89	19.5	13	FedEx
		11	ISFFWY0411IPS	"	"	"	9	"
6	6.625	07	ISFFWY0607IPS	35.5	6.38	27.9	38	FedEx
		11	ISFFWY0611IPS	"	"	"	27	"
		17	ISFFWY0617IPS	"	"	"	18	"
8	8.625	07	ISFFWY0807IPS	58	12	44	102	FedEx
		11	ISFFWY0811IPS	"	"	"	72	"
		17	ISFFWY0817IPS	"	"	"	64	"
10	10.75	07	ISFFWY1007IPS	58	13	44	133	LTL
		11	ISFFWY1011IPS	"	"	"	111	"
		17	ISFFWY1017IPS	"	"	"	75	"
12	12.75	07	ISFFWY1207IPS	64	16	48	245	LTL
		11	ISFFWY1211IPS	"	"	"	172	"
		17	ISFFWY1217IPS	"	"	"	115	"
14	14	07	ISFFWY1407IPS	64	16	48	295	LTL
		11	ISFFWY1411IPS	"	"	"	207	"
		17	ISFFWY1417IPS	"	"	"	139	"
16	16	07	ISFFWY1607IPS	73	19	54	437	LTL
		11	ISFFWY1611IPS	"	"	"	307	"
		17	ISFFWY1617IPS	"	"	"	206	"
18	18	07	ISFFWY1807IPS	73	19	54	554	LTL
		11	ISFFWY1811IPS	"	"	"	388	"
		17	ISFFWY1817IPS	"	"	"	261	"
20	20	07	ISFFWY2007IPS	109	22	87	1055	LTL
		11	ISFFWY2011IPS	"	"	"	883	"
		17	ISFFWY2017IPS	"	"	"	601	"
22	22	11	ISFFWY2211IPS	109	22	87	895	LTL
		17	ISFFWY2217IPS	"	"	"	601	"
24	24	09	ISFFWY2409IPS	109	22	87	1272	LTL
		11	ISFFWY2411IPS	"	"	"	1066	"
		17	ISFFWY2417IPS	"	"	"	716	"



1-800-345-ISCO
www.isco-pipe.com