

Part # **A2**

Clear
Flexible Polyolefin
2 to 1 Ratio
 (For colors use B2)



Specification Reference	
UL	○
VW-1	○
CSA	○
MIL Spec	● AMS-DTL-23053/5C Class 2

Replaces	
Raychem	RNF-100 Type 2
3M/ECC	FP301-C
Alpha	FIT-221-2

Description	A2 is a flexible, clear polyolefin heat shrinkable tubing (for colors use B2). Not flame retardant.
Uses	Uses requiring inspection (clear) or legibility of covered objects. Lightweight harnessing, strain relief and insulation of solder and crimp connections.
Operating Temp	-55°C, to +135°C, and up to 200°C, for short durations.
Shrink Temp	115°C
Standard Put-up	Spool *1/8", 3/16", & 1/4" also stocked in 4 foot lengths.

	Property (units)	Test Method	Requirements
Physical	Tensile Strength (psi)	ASTM D638	1500 MIN.
	Elongation (%)	ASTM D638	200 MIN.
	Specific gravity	ASTM D792	1.00 MAX.
	Low temp. flex (-55°C)	AMS-DTL-23053	No Cracking
	Heat shock (260°C, 4 Hrs.)	AMS-DTL-23053	No Cracking
	Heat resistance (175°C, 168 Hrs.) Elongation (%)	ASTM D638	100 MIN.
	Secant modulus (psi)	ASTM D882	25000 MAX.
	Longitudinal change	AMS-DTL-23053	±5
Electrical	Dielectric strength (volts/mil)	ASTM D876	500 MIN.
	Volume resistivity (ohm-cm)	ASTM D876	1.0 x 10 ¹⁴ MIN
Chemical	Corrosion (175°C, 16 Hrs.)	AMS-DTL-23053	No Corrosion
	Water absorption (%)	ASTM D570	0.2 MAX.
	Fluid resistance (23°C, 24 Hrs.) Tensile strength (psi)	AMS-DTL-23053	1000 MIN.
	Flammability		N/A
	Shrink Temperature (nominal)		110°C

Wholesale Pricing on Full Spools/Bags

Clear
Flexible Polyolefin
2 to 1 Ratio
(For colors use B2)

A2

Part #

Inside Diameter Before Shrinking (minimum)		Inside Diameter After Shrinking (maximum)	Post Shrink Wall Thickness	Full Spool Length	Price:	Color Selection											
						per spool	per foot	BK	BR	RD	OR	YL	GN	BL	VI	GY	WH
mm	inches	mm (inches)	mm (inches)	in feet		black	brown	red	orange	yellow	green	blue	violet	gray	white	clear	
1.2	3/64 0.0469	0.5842 (0.023)	0.4064 (0.016)	1000	\$348.50 \$0.41	X	X	X	X	X	X	X	X	X	X	●	
1.6	1/16 0.0625	0.7874 (0.031)	0.4318 (0.017)	1000	\$357.00 \$0.42	X	X	X	X	X	X	X	X	X	X	●	
2.4	3/32 0.0938	1.1684 (0.046)	0.508 (0.020)	500	\$187.00 \$0.44	X	X	X	X	X	X	X	X	X	X	●	
3.2	1/8 0.1250	1.5748 (0.062)	0.508 (0.020)	*500	\$195.50 \$0.46	X	X	X	X	X	X	X	X	X	X	●	
4.8	3/16 0.1875	2.3622 (0.093)	0.508 (0.020)	*200	\$96.90 \$0.57	X	X	X	X	X	X	X	X	X	X	●	
6.4	1/4 0.250	3.175 (0.125)	0.635 (0.025)	*200	\$119.00 \$0.70	X	X	X	X	X	X	X	X	X	X	●	
9.5	3/8 0.375	4.7498 (0.187)	0.635 (0.025)	200	\$134.30 \$0.79	X	X	X	X	X	X	X	X	X	X	●	
12.7	1/2 0.500	6.350 (0.250)	0.635 (0.025)	200	\$154.70 \$0.91	X	X	X	X	X	X	X	X	X	X	●	
15.9	5/8 0.625	7.9375 (0.3125)	0.762 (0.030)	200	\$202.30 \$1.19	X	X	X	X	X	X	X	X	X	X	●	
19.1	3/4 0.750	9.525 (0.375)	0.762 (0.030)	200	\$205.70 \$1.21	X	X	X	X	X	X	X	X	X	X	●	
25.4	1.000 1.000	12.700 (0.500)	0.889 (0.035)	200	\$307.70 \$1.81	X	X	X	X	X	X	X	X	X	X	●	
31.8	1-1/4 1.250	15.875 (0.625)	1.016 (0.040)	200	\$559.30 \$3.29	X	X	X	X	X	X	X	X	X	X	●	
38.1	1-1/2 1.500	19.050 (0.750)	1.0160 (0.040)	200	\$508.30 \$2.99	X	X	X	X	X	X	X	X	X	X	●	
50.8	2.000 2.000	25.400 (1.000)	1.143 (0.045)	200	\$703.80 \$4.14	X	X	X	X	X	X	X	X	X	X	●	
76.2	3.000 3.000	38.100 (1.500)	1.270 (0.050)	200	\$1,417.80 \$8.34	X	X	X	X	X	X	X	X	X	X	●	
101.6	4.000 4.000	50.800 (2.000)	1.397 (0.055)	100	\$921.40 \$10.84	X	X	X	X	X	X	X	X	X	X	●	

Available in Clear Only
(For colors use B2)

Lead Time: 1 day	Lead Time: up to 50 days	Lead Time: up to 100 days	Lead Time: up to 200 days	Not Possible

The above lead time guidelines are estimated only. They may be longer (not usually) or they may be shorter (typically). Regarding products with 100 & 200 day lead time; pricing may vary, and a minimum order with deposit may be required. Oh... and by the way, everything can change without notice and/or liability.