

Eco-Lag Adhesive 11-30



COLOR

Off White

SERVICE TEMPERATURE

-40 to 180°F (-40 to 82°F)

COVERAGE

80 to 100 sq. ft./gal.

The coverage rate is dependent on the surface being covered and the application method used.

WEIGHT PER GALLON

10 lb

AVERAGE NONVOLATILE

45.6% by weight 47.5% by volume

BONDING TIME

0 to 10 min.

Note: Drying time varies with adhesive thickness, temperature, and humidity.

SAFETY

Flammability Wet: Non-flammable Dry: See UL Classification

LIMITATIONS

Keep from freezing. Apply between 40°F (4°C) and 110°F (43°C)

CAUTION:

Use with adequate ventilation. Avoid prolonged or repeated breathing of vapor. Avoid prolonged or repeated contact with skin. Do not take internally. In an emergency, call a physician. Keep out of reach of children.

MAX VOC=0.21 lbs/gal or 26 gms/Liter

DESCRIPTION

11-30 Eco-Lag Adhesive is a water based lagging adhesive for adhering and sizing canvas, glass cloth and other textile jacketing materials on thermal insulation. It dries to form a suitable surface for further finishing.

METHOD OF APPLICATION

Brush, dip, spray

MATERIAL PREPARATION

Stir 11-30 before using it.

APPLICATION

This product is for industrial use only. It should be applied by trained and qualified craftspeople. Apply to clean, oil-free surfaces. To seal indoor concealed piping brush **11-30** to all canvas laps at a rate of 90 sq. ft./gal. Smooth out fabric. Apply the top coat evenly at a rate of 90 sq. ft./gal.

To seal exposed equipment apply a tack coat of **11-30** at 90 sq. ft./gal. Embed the lagging cloth into the wet tack coat. Overlap and seal all seams. Apply a top coat of 11-30 at a coverage of 90 sq. ft./gal.

CLEANUP

Wet: Clean, fresh water

Dry: Hot, soapy water or a string solvent.

ASBESTOS FREE

UNDERWRITERS LABORATORIES, INC.[®]
CLASSIFIED
ADHESIVE SURFACE BURNING CHARACTERISTICS
66H9

R10070 Applied to inorganic Reinforced Cement Board

Flame Spread 10 10 10 Smoke Developed 0 0 Tested as applied at a coverage rate of 100 sq. ft./gal. (2.5m²/L)

WARRANTY TERMS: The physical and chemical properties of this product are representative of the typical average values derived in accordance with test methods deemed acceptable, and can vary when subjected to normal manufacturing methods. These values are supplied only as a technical service and are subject to change without notice. To be sure information is current call Mon-Eco Industries, Inc.

Terms of Warranty: Warrantor, Mon-Eco Industries, Inc. warrants satisfactory results of this product only when recommendations herein established are followed. The recommendations for use are established upon tests and information deemed reliable. We recommend that adequate testing be made by the user to determine if the product is suitable for the intended purpose and use. Warrantor assumes no responsibility beyond replacement or refund of the purchase price of this product, since warrantor has no control over the methods and application of its product, methods and conditions of transportation, handling and storage of the product. WARRANTOR EXPLICITLY DISCLAIMS ALL LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGE. No agent or representative of Mon-Eco Industries, Inc. has the authority to change or extend these conditions.

Mon-Eco Industries, Inc.

8/08





