



M E I ADHESIVE 22-43

**COLOR**

Amber

SERVICE TEMPERATURE

-30°F to 190°F

WEIGHT PER GALLON

6.4 lbs.

COVERAGE

400 sq. ft./gal.

The coverage is dependent on the surface being covered and the application method.

AVERAGE NONVOLATILE

30% (approx)

BONDING RANGE

0 to 5 minutes

The drying time depends on the temperature, humidity and film thickness.

SAFETY

Wet: Flash point - 4°F. Red Label

Dry: 22-43 is U.L. Classified.

WARNING

Flammable Mixture Red Label. Do not use or store near heat, sparks, or open flame, Use with adequate ventilation. Avoid prolonged or repeated breathing of vapor. Avoid prolonged or repeated contact with skin. In an emergency, call a physician. Keep out of reach of children.

ASBESTOS FREE**DESCRIPTION**

22-43 M E I Adhesive is a spray adhesive suitable for air atomizing or airless spray equipment. It is designed to provide quick, strong tack for adhering fiberglass to itself and to various jacketing materials.

LIMITATIONS

Do not apply below 40°F or above 110°F. Some plastic foams may be attacked by the solvent in 22-43. Test before using.

METHOD OF APPLICATION

Spray, roller, or brush

APPLICATION

This product is for industrial use only. It should be applied by trained and qualified craftspeople. Be sure surfaces are clean and dry. Apply 22-43 in a thin uniform coat. As tack develops firmly press the insulation into it.

MATERIAL PREPARATION

Do not thin. Stir well.

CLEANUP

Mineral spirits or chlorinated solvent

**UNDERWRITERS LABORATORIES, INC.®
CLASSIFIED****ADHESIVE SURFACE BURNING CHARACTERISTICS
66H9**

R10070	Applied to Inorganic Reinforced Cement Board		
		<u>USC</u>	<u>CNC</u>
Flame Spread		15	10
Smoke Developed		0	0
Coverage Rate of 400 sq. ft./gal. (9.8 m2/L)			
Flash point of liquid adhesive. Closed cup. No less than -20°F.			

Warranty Terms: The physical and chemical properties of this product are representative of the typical average values derived in accordance with test methods deemed acceptable, and can vary when subjected to normal manufacturing methods. These values are supplied only as a technical service and are subject to change without notice. To be sure information is current call Mon-Eco Industries, Inc.

Terms of Warranty: Warrantor, Mon-Eco Industries, Inc. warrants satisfactory results of this product only when recommendations herein established are followed. The recommendations for use are established upon tests and information deemed reliable. We recommend that adequate testing be made by the user to determine if the product is suitable for the intended purpose and use. Warrantor assumes no responsibility beyond replacement or refund of the purchase price of this product, since warrantor has no control over the methods and application of its product, methods and conditions of transportation, handling and storage of the product. WARRANTOR EXPLICITLY DISCLAIMS ALL LIABILITY FOR INCIDENTAL OR CONSEQUENTIAL DAMAGE. No agent or representative of Mon-Eco Industries, Inc. has the authority to change or extend these conditions.

Mon-Eco Industries, Inc.

5 Joanna Court • 800-899-6326 • East Brunswick, NJ 08816 732 257-7942 Fax: 732-257-6525