

SHEETROCK® Lightweight Setting-Type Joint Compounds

EASY SAND™



For one-day drywall finishing

- For interior gypsum panels and exterior gypsum ceiling boards.
- Weighs 25% less than conventional setting-type compounds.
- Sanding ease similar to a ready-mixed, all-purpose joint compound.
- Unique humidity resistance.
- Exceptional bond with low shrinkage.
- Check-crack resistance in heavy fills.
- Choice of setting times.

Description

SHEETROCK® Brand EASY SAND™ Lightweight Setting-Type Joint Compounds are nonasbestos, chemically setting compounds for drywall interiors and exteriors that permit same-day joint finishing, and, usually, next-day decoration. Compounds are lightweight for easy handling and sand easily for fast, smooth finishing. They are ideal for heavy fills and are virtually unaffected by humidity. They provide low shrinkage and superior bond, which makes them excellent for laminating gypsum panels to gypsum panels, to sound-deadening boards, and to above-grade concrete surfaces. In addition, they can be used for filling, smoothing, and finishing interior concrete ceilings and above-grade concrete, and for finishing joints in exterior gypsum ceiling boards.

To meet varying job requirements, a full line has been developed to provide a choice in setting times. The suffix number identifying each joint compound indicates an approximate setting time. For example, EASY SAND 90 sets in approximately 85-130 minutes. Other setting times available are 20 (20-30 minutes); 45 (30-80 minutes); 210 (180-240 minutes); and 300 (240-360 minutes). For patching applications requiring very quick setting, SHEETROCK® Brand EASY SAND™ 5 Patching Compound, with a setting time of 8-12 minutes, is available.

Advantages

Lightweight formula. Weighs 25% less than conventional setting-type joint compounds. Handling and application is simpler, easier, and faster.

Easy sanding. Unlike conventional setting-type joint compounds, these compounds sand easily—similar to ready-mixed, all-purpose joint compounds. Joint finishing is faster, easier, smoother.

Saves time and money. These compounds provide important labor and material cost reductions. One-day finishing with next-day decoration ensures rapid job completion and earlier occupancy. Choice of setting times aids work flow.

Quickly mixed for immediate use. Easy to mix—simply combine with water and stir. Compounds are applied after short soaking period and remixing.

Resists shrinkage and edge-cracking. Compounds tolerate small amounts of excess water that would otherwise cause delayed shrinkage. Fill and finish coats can be applied when compound is hard—but still damp—with minimum danger of delayed shrinkage and cracking.

Resists humidity changes. Setting rates are virtually unaffected by high humidity or changes in humidity. Application can be made in damp weather when drying-type compounds would delay job completion.

Multiple use. Compounds are also excellent for patching and smoothing interior drywall and concrete surfaces because they provide superior bond, low shrinkage, and fast setting-action.

Limitations

1. Setting action cannot be delayed or prevented by dilution with water.
2. Not to be applied over moist surfaces or surfaces likely to become moist, or on below-grade surfaces or surfaces projecting outside building structure unless protected from direct exposure to moisture.
3. Before using over new interior concrete surfaces, allow concrete to age 60 days or more. Remove protrusions, ridges, form or parting oils, grease, and efflorescence.
4. Prior to using any epoxy coating over any surface treated with joint compound, consult the epoxy coating manufacturer and follow manufacturer's specific recommendations regarding the preparation or suitability of substrates for the epoxy coating. Many epoxy coatings exert significant shear stress on the substrate as the strong epoxy film shrinks while curing/drying. This stress can cause the bond of the joint compound to fail, resulting in delamination problems.

Directions	Preparation	In cold weather during gypsum panel joint finishing, minimum surface, water, mix, and air temperature of 45 °F must be ensured until joints are completely dry. Adequate ventilation shall be provided to carry off excess moisture.
	Gypsum Panel Joint Treatment	<p>Position and apply SHEETROCK® Brand Gypsum Panels in accordance with manufacturer's recommendations. Mix compound according to directions on bag. If using SHEETROCK® Brand Gypsum Panels, SW Edge, prefill the "V" grooves formed by abutting tapered eased edges of the panels with EASY SAND 45 or 90. Apply compound directly over "V" groove with a flexible 5" or 6" joint finishing knife. Wipe off excess compound that is applied beyond the groove. Allow prefill compound to harden prior to the next application (tape-embedding coat).</p> <p>Cover joint with a thin layer of compound and embed tape, leaving about 1/32" of compound under feathered edge and a thin layer over the tape. After compound has set, apply second coat, feathering out approximately 2" beyond first coat. After setting, apply third coat, feathering out 2" beyond second coat. After each coat is applied, smooth away any tool lap marks or other imperfections prior to hardening action. Finish fastener heads with three coats of joint compound; finish corner bead and inside corners as required with at least two coats, feathered and smoothed out onto panel faces.</p> <p>For priming and decorating with paint, texture, or wallcovering, follow manufacturer's directions for materials used. All surfaces must be dry, dust-free, and not glossy. A prime coat of SHEETROCK® Brand First Coat or a good-quality interior latex flat wall paint with high solids content should be applied undiluted and allowed to dry before decorating. Walls to be covered with wallpaper or vinyl wallcovering should be sealed per manufacturer's recommendations. To improve fastener concealment where gypsum panel walls and ceilings will be subjected to severe artificial or natural side lighting and decorated with a gloss paint (eggshell, semigloss, or gloss), the gypsum panel surface should be skim-coated with joint compound to equalize suction before painting (see publication J510).</p>
	Filling and Finishing over Interior Poured Ceilings	Grind high plane differences in concrete level with adjacent area; also remove any form of oil, efflorescence, and greasy deposits. Prime exposed metal with a good rust-inhibitive primer. Fill offsets or voids with joint compound. Apply additional coats of joint compound as necessary, after each coat has set, but not necessarily dried. After the final coat of joint compound has dried, apply an undiluted coat of SHEETROCK Brand First Coat or a good quality latex flat wall paint with high solids content over entire surface and allow to dry. For textured ceiling, apply SHEETROCK® Brand Ceiling Spray Texture—QT in a uniform coat at a rate not exceeding 10 ft. ² /lb.
	Exterior Joint Treatment	Mix joint compound according to directions on the bag. Do not overmix or use at temperatures below 45 °F (7 °C). Prefill joints of SHEETROCK® Brand Exterior Gypsum Ceiling Board with compound. After prefill has set, embed SHEETROCK Brand Joint Tape centered over joint. When compound has set, immediately apply fill coat. Apply compound over flanges of zinc control joints, corner beads, and metal trim. Spot fastener heads. After fill coat has set, apply finishing coat of compound. Completely cover all joints, angles, beads, control joints, and fasteners. After the compound has dried, apply one coat of a good-quality oil or latex exterior primer. Then follow with at least one coat of a good-quality latex exterior paint.
	Laminating	Apply joint compound in the prescribed manner to back of face panels to be laminated. Laminate face panels to (base layer panels) (coreboard) using moderate pressure and temporary nailing or shoring to ensure adequate bond.
	Finishing	For painting and decorating, follow manufacturer's directions for materials used.

Use With USG Gypsum Accelerator

USG™ Gypsum Accelerator (High Strength) will shorten the setting time when added to EASY SAND Joint Compound. USG Gypsum Accelerator should be sprinkled in dry form into the mixed compound. For hand mixing, dry accelerator can be added either to the dry mix or mixed compound. Never add USG Gypsum Accelerator directly to water or mix it with water to form a solution before adding it to the compound. Doing so will significantly reduce its ability to accelerate the set.

Accelerator Amount		Approximate Set Time (minutes)		
Tablespoon Per Bag	Tablespoon Per Bread Pan	EASY SAND 90	EASY SAND 45	EASY SAND 20
1.0	0.22	40	20	10
2.0	0.44	30	10	
6.0	1.33	20		

- "Bread Pan" volume estimated at 10 cups (80 oz.)
- Wet Mixed Volume of Setting Type Joint Compounds approx. 2.8 gallons (45 cups) per bag.

Product Data

Color: Natural.

Binder: Vinyl.

Filler: Calcium Sulfate.

Dilution (water): Approximately 10 to 12 pts./18 lb. (4.6 to 5.6 L/8.1 kg). Refer to bag for specific water dilution directions.

Density (dry bulk): 32 lb./ft.³ (513 kg/m³).

Freezing Sensitivity: None after set, but not necessarily dry.

Coverage: Average 52 lb./1000 ft.² (25.3 kg/100 m²) of gypsum panels.

Compliance with Standards: Meet ASTM Standard C475.

Storage: Close open bags as tightly as possible and store in a dry place.

Shelf Life: Up to 6 months under protected storage conditions.

Packaging: 18 lb. (8.1 kg) bags for EASY SAND 5, 20, 45, 90, 210 and 300; 4 lb. (1.8 kg) boxes for EASY SAND 5 and 90.

Submittal Approvals:

Job Name	
Contractor	Date

WARNING

When mixed with water, this material hardens and then slowly becomes hot. Do not attempt to make a cast enclosing any part of the body using this material. Failure to follow these instructions may cause severe burns that may require surgical removal of affected tissue. Avoid inhalation of dust and eye contact. Dust generated by sanding may cause eye, skin, or respiratory tract irritation. Use wet-sanding to avoid creating dust. If dusty,

wear a NIOSH/MSHA-approved respirator. Prolonged and repeated exposure to mica may cause lung disease. Wear eye protection. If eye contact occurs flush thoroughly with water for 15 minutes. If irritation persists, call physician. Do not ingest. If ingested, call physician. Product safety information: (800) 507-8899.

KEEP OUT OF REACH OF CHILDREN.

Trademarks

The following trademarks used herein are owned by United States Gypsum Company: EASY SAND, SHEETROCK, USG.

Note
Products described here may not be available in all geographic markets. Consult your U.S. Gypsum Company sales office or representative for information.

Notice

We shall not be liable for incidental and consequential damages, directly or indirectly sustained, nor for any loss caused by application of these goods not in accordance with current printed instructions or for other than the intended use. Our liability is expressly limited to replacement of defective goods. Any claim shall be deemed waived unless made in writing to us within thirty (30) days from date it was or reasonably should have been discovered.

SAFETY FIRST!

Follow good safety and industrial hygiene practices during handling and installation of all products and systems. Take necessary precautions and wear the appropriate personal protective equipment as needed. Read material safety data sheets and related literature on products before specification and/or installation.

