



StretchKote

Interior / Exterior Elastomeric Coating



STRETCHKOTE™ is a premium, integrally colored elastomeric based decorative and protective coating that provides excellent crack bridging qualities. StretchKote™ is available in multiple colors. All UltraKote's finishes and coatings contain additives to resist Mildew, Algae, and Fungus.

Product Specifications:

Packaging:

5 gallon plastic pail
– 52 lbs. (22.6 kg.)

Coverage:

Approximate coverage is 225-350 sq. ft. per pail @ 10 mils. Dry thickness. Two coats may be necessary to achieve the recommended mill thickness.

Coverage can also vary depending on substrate, surface texture and application technique.

Color:

All UltraKote Standard Colors and Custom colors on written request.

Storage:

Store in cool dry place away from direct sunlight.

Clean up:

Store in cool dry place away from direct sunlight.

Shelf Life:

1 year

Uses:

STRETCHKOTE™ is an exterior elastomeric paint with high elongation properties for bridging cracks in masonry, concrete, stucco or synthetic substrates. StretchKote offers excellent weather resistance. A siliconized version is available by special order



Features:

- Weather Resistant
- Crack bridging
- Silicone Version

Benefits:

- Greater protection for longer periods
- Greater flexibility for longer life
- Increased ease in surface cleaning

August 2009

UltraKote Products, Inc.
327 South 27th Avenue, Phoenix, Arizona 85009
Phone: 800.224.2344 Fax: 602.272.6445

www.ultrakoteproducts.com

StretchKote

Interior / Exterior Elastomeric Coating

Coatings / Primers

Surface Preparation:

Surface must be clean and free of bond-inhibiting materials such as dirt, dust, rust, grease, oil, efflorescence, mildew, fungus, form-release agents, or any other contaminants. Remove and repair any loose paint, mortar, stucco, concrete or masonry by water blasting, sand blasting, scraping or using a wire brush. Repair all cracks with a proper patching compound. If applying over a painted surface, test paint to ensure it is load bearing.

Mixing:

Prior to use mix until the desired consistency is achieved. One quart (16 oz.) of potable water may be added to 5 gallons of STRETCHKOTE.

Application:

STRETCHKOTE may be applied by roller, brush or spray equipment (spray tip should be a 5-19 through a 6-23). Always apply STRETCHKOTE in a continuous application, working to a wet edge to eliminate cold joints.

Curing / Drying:

Drying time averages 3 hours depending on ambient temperature, humidity and film thickness. STRETCHKOTE will dry completely within 12 hours.

Limitations:

STRETCHKOTE should be applied when surface and ambient conditions are between 45°F and 100°F and protected from wet weather for 24 hours. Substrates must have a pH 12 or lower. STRETCHKOTE has excellent bonding to almost any surface except certain plastics, rubber, metal and mastics. Glossy surfaces should be sanded prior to application



Precautions:

KEEP OUT OF THE REACH OF CHILDREN.
Not for internal consumption.
Do not apply in non-ventilated area.
Use protective equipment such as gloves, eye protection and clothing.

First Aid:

In case of eye contact, flush with water at least 15 minutes.
In case of skin contact, wash affected areas with soap and water. If irritation persists, SEEK MEDICAL ATTENTION. Remove and wash contaminated clothing.
If inhalation causes physical discomfort, remove to fresh air. If discomfort continues, any breathing difficulty occurs or if swallowed, SEEK IMMEDIATE MEDICAL ATTENTION.
For additional information refer to the Material Safety Data Sheet (MSDS).

Disposal:

Dispose of in accordance with local, state or federal regulations.

Warning:

KEEP OUT OF REACH OF CHILDREN.
NOT FOR INTERNAL CONSUMPTION,
FOR INDUSTRIAL USE ONLY

Spills:

Scrape up and wash with water immediately. If material has set, scrape material with appropriate tools and clean with citric acid.

Prop 65:

This product contains materials listed by the state of California known to cause cancer, birth defects, or other reproductive harm.

Technical Support:

For technical support call 1-602-272-5830. Information contained in this Product Information Guide conforms to the standard detail recommendations and specifications for the installations of UltraKote products as of the date published on this document. UltraKote Products, Inc. assumes no liability, expressed or implied, as to the architecture, engineering or workmanship of any project. To insure that you are using the latest, most current information, contact UltraKote Products, Inc. or visit website at www.ultrakoteproducts.com.

August 2009

UltraKote Products, Inc.
327 South 27th Avenue, Phoenix, Arizona 85009
Phone: 800.224.2344 Fax: 602.272.6445

www.ultrakoteproducts.com